



TECHNICAL DATA SHEET

CORAPLAST WHITE MASTER BATCH

MASTERBATCH INFORMATION	
1. PRODUCT CODE	WE-279
2. COLOUR	WHITE 30
3. BASE POLYMER	PE

PROPERTIES	
1. LIGHT FASTNESS	7 - 8
2. HEAT STABILITY TEMP. (°C)	280° C
3. MIGRATION	5
4. TiO ₂ CONTENT	30.00 % Equivalent
5. ASH CONTENT %	80.00 ± 2.00 %
6. MOISTURE CONTENT	< 0.20 % (Temp 120°C 10Min)
7. BULK DENSITY	1.20 ± 0.1Gm/ml
8. MFI (Load 5.00 kg Temp 190°C) ASTM	30.00 ± 10.00 Gm/10 Min.
9. FOOD CONTACT COMPLIANCE	Applicable

GENERAL INFORMATION	
1. PACKING	25Kg bag
2. STORAGE	Material must be storage in dry area at normal room

Note : The above data are derived from our laboratory tests and true to the best of our knowledge and belief. The above data should be used purely as guidelines and should not be considered as warranty. This technical information consists of typical product data and should not be used as a specification. The above information and description are subject to change without notice.

31-36,
Premier Industrial Estate,
Kachigam Daman-396 210.

Tel.: + 91(260) 2243545, 2244977
Fax : + 91(260) 2243445
E-mail: sales.bi@colourtex.co.in
www.coroplast.co.in



TECHNICAL DATA SHEET

CORAPLAST WHITE MASTER BATCH

MASTERBATCH INFORMATION	
1. PRODUCT CODE	WE-280
2. COLOUR	WHITE 40
3. BASE POLYMER	PE

PROPERTIES	
1. LIGHT FASTNESS	7 - 8
2. HEAT STABILITY TEMP. (°C)	280° C
3. MIGRATION	5
4. TiO ₂ CONTENT	40.00 % Equivalent
5. ASH CONTENT %	80.00 ± 2.00 %
6. MOISTURE CONTENT	< 0.20 % (Temp 120°C 10Min)
7. BULK DENSITY	1.20 ± 0.1Gm/ml
8. MFI (Load 5.00 kg Temp 190°C) ASTM	30.00 ± 10.00 Gm/10 Min.
9. FOOD CONTACT COMPLIANCE	Applicable

GENERAL INFORMATION	
1. PACKING	25Kg bag
2. STORAGE	Material must be storage in dry area at normal room

Note : The above data are derived from our laboratory tests and true to the best of our knowledge and belief. The above data should be used purely as guidelines and should not be considered as warranty. This technical information consists of typical product data and should not be used as a specification. The above information and description are subject to change without notice.

31-36,
Premier Industrial Estate,
Kachigam Daman-396 210.

Tel.: + 91(260) 2243545, 2244977
Fax : + 91(260) 2243445
E-mail: sales.bi@colourtex.co.in
www.coraplast.co.in



TECHNICAL DATA SHEET

CORAPLAST WHITE MASTER BATCH

MASTERBATCH INFORMATION	
1. PRODUCT CODE	WE-281
2. COLOUR	WHITE 50
3. BASE POLYMER	PE

PROPERTIES	
1. LIGHT FASTNESS	7 - 8
2. HEAT STABILITY TEMP. (°C)	280° C
3. MIGRATION	5
4. TiO ₂ CONTENT	50.00 % Equivalent
5. ASH CONTENT %	80.00 ± 2.00 %
6. MOISTURE CONTENT	< 0.20 % (Temp 120°C 10Min)
7. BULK DENSITY	1.30 ± 0.1Gm/ml
8. MFI (Load 5.00 kg Temp 190°C) ASTM	25.00 ± 10.00 Gm/10 Min.
9. FOOD CONTACT COMPLIANCE	Applicable

GENERAL INFORMATION	
1. PACKING	25Kg bag
2. STORAGE	Material must be storage in dry area at normal room

Note : The above data are derived from our laboratory tests and true to the best of our knowledge and belief. The above data should be used purely as guidelines and should not be considered as warranty. This technical information consists of typical product data and should not be used as a specification. The above information and description are subject to change without notice.

31-36,
Premier Industrial Estate,
Kachigam Daman-396 210.

Tel.: + 91(260) 2243545, 2244977
Fax : + 91(260) 2243445
E-mail: sales.bi@colourtex.co.in
www.coraplast.co.in



TECHNICAL DATA SHEET

CORAPLAST WHITE MASTER BATCH

MASTERBATCH INFORMATION	
1. PRODUCT CODE	CP-8A-282F
2. COLOUR	WHITE 60
3. BASE POLYMER	PE

PROPERTIES	
1. LIGHT FASTNESS	7 - 8
2. HEAT STABILITY TEMP. (°C)	280° C
3. MIGRATION	5
4. TiO ₂ CONTENT	60.00 % Equivalent
5. ASH CONTENT %	80.00 ± 2.00 %
6. MOISTURE CONTENT	< 0.20 % (Temp 120°C 10Min)
7. BULK DENSITY	1.40 ± 0.1Gm/ml
8. MFI (Load 5.00 kg Temp 190°C) ASTM	50.00 ± 10.00 Gm/10 Min.
9. FOOD CONTACT COMPLIANCE	Applicable

GENERAL INFORMATION	
1. PACKING	25Kg bag
2. STORAGE	Material must be storage in dry area at normal room

Note : The above data are derived from our laboratory tests and true to the best of our knowledge and belief. The above data should be used purely as guidelines and should not be considered as warranty. This technical information consists of typical product data and should not be used as a specification. The above information and description are subject to change without notice.

31-36,
Premier Industrial Estate,
Kachigam Daman-396 210.

Tel.: + 91(260) 2243545, 2244977
Fax : + 91(260) 2243445
E-mail: sales.bi@colourtex.co.in
www.coraplast.co.in



TECHNICAL DATA SHEET

CORAPLAST WHITE MASTER BATCH

MASTERBATCH INFORMATION	
1. PRODUCT CODE	CP-8A-283F
2. COLOUR	WHITE 70
3. BASE POLYMER	PE

PROPERTIES	
1. LIGHT FASTNESS	7 - 8
2. HEAT STABILITY TEMP. (°C)	280° C
3. MIGRATION	5
4. TiO ₂ CONTENT	70.00 % Equivalent
5. ASH CONTENT %	80.00 ± 2.00 %
6. MOISTURE CONTENT	< 0.20 % (Temp 120°C 10Min)
7. BULK DENSITY	1.40 ± 0.1Gm/ml
8. MFI (Load 5.00 kg Temp 190°C) ASTM	30.00 ± 10.00 Gm/10 Min.
9. FOOD CONTACT COMPLIANCE	Applicable

GENERAL INFORMATION	
1. PACKING	25Kg bag
2. STORAGE	Material must be storage in dry area at normal room

Note : The above data are derived from our laboratory tests and true to the best of our knowledge and belief. The above data should be used purely as guidelines and should not be considered as warranty. This technical information consists of typical product data and should not be used as a specification. The above information and description are subject to change without notice.

31-36,
Premier Industrial Estate,
Kachigam Daman-396 210.

Tel.: + 91(260) 2243545, 2244977
Fax : + 91(260) 2243445
E-mail: sales.bi@colourtex.co.in
www.coroplast.co.in



TECHNICAL DATA SHEET

CORAPLAST ADDITIVES MASTER BATCH

MASTERBATCH INFORMATION	
1. PRODUCT CODE	AB 222
2. PRODUCT NAME	ANTI BLOCK MB
3. BASE POLYMER	PE

PROPERTIES	
1. LIGHT FASTNESS	-----
2. HEAT STABILITY TEMP. (°C)	300 -----
3. MIGRATION	-----
4. ACTIVE CONTENT %	20.00 ± 2.00 %
5. MOISTURE CONTENT	< 0.20 % (Temp 120°C 10Min)
6. BULK DENSITY	0.60 ± 0.1 Gm/ml
7. MFI (Load 2.16 kg Temp 190°C) ASTM	15.00 ± 5.00 Gm/10 Min.
8. FOOD CONTACT COMPLIANCE	Applicable

GENERAL INFORMATION	
1. PACKING	25Kg bag
2. STORAGE	Material must be storage in dry area at normal room

Note : The above data are derived from our laboratory tests and true to the best of our knowledge and belief. The above data should be used purely as guidelines and should not be considered as warranty. This technical information consists of typical product data and should not be used as a specification. The above information and description are subject to change without notice.